

# Technical Data Sheet

## 401 Fiberglass Pipe Repair Tape

**UNIGRIP**  
DANTECH ELITE COMPOSITES

### Technical data and performance

Curing Time at 20°C (68°F)	
Working Time	3-5 minutes
Cured material life	10-20 years dependent on repair quality, environmental conditions, pipe temperature etc.
Initial Cure Time	7-10 minutes
Full cure Time	30minutes

Mechanical Properties	
Tensile Strength	5075psi
Pressure resistance	145psi / 10 bar (Based on 9 layers) 450psi / 31 bar (when used with putty)
Shore D Hardness	70

Appearance	
Single Pack	Color White

Shelf Life	
3 Years	If unopened and stored in normal dry conditions 60-86 °F (15-30°C)

Maximum Heat	
Continuous: 150°C (300°F)	Peak: 190°C (374°F)

### Chemical resistance

·Please consult the Unigrip pipe tape / chemical resistance list

### For best results:

Do not apply when:

- The temperature is below 41 °F (5 °C)
- The working surface are not yet prepared acc. to UNIGRIP guidelines
- The working surface is contaminated by dirt/oil/grease etc.

### Safety data:

·For additional health and safety information, consult a Safety Data Sheet.